

**SLIP RESISTANCE DETERMINATION OF SELF-ADHESIVE FLOORING FILM**

Hexis Product Name: V650T

**EXPERIMENTAL DETAILS**

Samples were tested in accordance with the following standards, except as otherwise noted. Tests were carried out on both dry and wet samples.

**T.R.R.L Pendulum Tester**

Testing was carried out in accordance with specification BS6677: Part1:1986 for the measurement of floor slip resistance utilising the RAPRA Four S Slider.

**UK SLIP RESISTANCE GROUP LIMITS**

<u>Four S Pendulum Value</u>	<u>Potential for Slip</u>
25 and below	HIGH
25 to 35	MODERATE
35 to 65	LOW
above 65	EXTREMELY LOW

**RESULTS FOR SANDTEX FG**

<u>Four S Pendulum Value</u>	<u>Potential for Slip</u>
DRY            72	EXTREMELY LOW
WET            50	LOW

**DISCUSSION**

Test results show extremely low risk of slip when dry and low risk when wet.

Results do not take into account "wear" over time and the condition of the many different floor surfaces for which the product may be applied.